

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1-7. (cancelled)

8. (currently amended) A mold for making a composite material part, ~~the mold being coated in a stripping composition~~ comprising:

a coating of a stripping composition on the mold, wherein the stripping composition comprises:

- 100 parts by weight of a base ingredient constituted by an epoxy polydimethylsiloxane;

- 0.5 to 10 parts by weight of a polymerization agent for polymerizing the base ingredient and constituted by a diaryliodonium salt;

- an anti-adhesion modulator constituted by a silicone polymer, present at a concentration of ~~not more than 30~~ 5 to 10 parts by weight; and

- an anti-stick agent making the composition less tacky prior to polymerization, constituted at least by a vinyl ether compound, which is present at a concentration of ~~not more than 40~~ 8 to 12 parts by weight.

9. (currently amended) [[A]] The mold according to claim 8, wherein said anti-adhesion modulator is also constituted by an epoxy polydimethylsiloxane.

10-12. (cancelled)

13. (currently amended) [[A]] The mold according to claim 8, wherein

said stripping composition has ~~5~~ 5 to 7 parts by weight of the polymerization agent;

~~5 to 10 parts by weight of the anti-adhesion modulator,~~ said anti-adhesion modulator being is an epoxy polydimethylsiloxane; and

• the anti-stick agent ~~being present at~~ comprises a concentration in the range 8 to 12 parts by weight of a dodecyl monovinyl ether and 8 to 12 parts by weight of a cyclohexane dimethanol divinyl ether.

14. (currently amended) [[A]] The mold according to claim 13, wherein the stripping composition has:

- 6 parts by weight of the polymerization agent;
- 8 parts by weight of the anti-adhesion modulator; and
- the anti-stick agent ~~being present at~~ comprises a concentration of 11.4 parts by weight of a dodecyl monovinyl

ether and 11.4 parts by weight of a cyclohexane dimethanol divinyl ether.

15. (previously presented) A wipe or cloth impregnated in a stripping composition presenting the characteristics of claim 8.

16. (currently amended) A method of molding a composite material part, comprising:

forming a composite material in a mold coated by a stripping composition, wherein the mold is coated in a stripping composition comprising comprises:

- 100 parts by weight of a base ingredient constituted by an epoxy polydimethylsiloxane;

- 0.5 to 10 parts by weight of a polymerization agent for polymerizing the base ingredient and constituted by a diaryliodonium salt;

- an anti-adhesion modulator constituted by a silicone polymer, present at a concentration of ~~not more than 30~~ 5 to 10 parts by weight; and

- an anti-stick agent making the composition less tacky prior to polymerization, constituted at least by a vinyl ether compound, which is present at a concentration of ~~not more than 40~~ 8 to 12 parts by weight.

.

17. (currently amended) [[A]] The method according to claim 16, wherein said anti-adhesion modulator is also constituted by an epoxy polydimethylsiloxane.

18-20. (canceled)

21. (currently amended) [[A]] The method according to claim 16, wherein

said stripping composition has ~~5~~ 5 to 7 parts by weight of the polymerization agent;

~~5 to 10 parts by weight of the anti-adhesion modulator,~~ said anti-adhesion modulator ~~being~~ is an epoxy polydimethylsiloxane; and

the anti-stick agent ~~being present at~~ comprises a concentration in the range 8 to 12 parts by weight of a dodecyl monovinyl ether and 8 to 12 parts by weight of a cyclohexane dimethanol divinyl ether.

22. (currently amended) [[A]] The method according to claim 21, wherein said stripping composition has:

- 6 parts by weight of the polymerization agent;
- 8 parts by weight of the anti-adhesion modulator; and

· the anti-stick agent being present at a concentration of 11.4 parts by weight of a dodecyl monovinyl ether and 11.4 parts by weight of a cyclohexane dimethanol divinyl ether.

23. (currently amended) [[A]] The method according to claim 16, wherein the surface of the mold is coated with the stripping composition to a thickness of micrometer order.

24. (currently amended) [[A]] The method according to claim 16, wherein the surface of the mold is coated with a wipe or a cloth impregnated in the stripping composition.

25. (currently amended) [[A]] The method according to claim 16, wherein the stripping composition is polymerized under the action of ultraviolet radiation.

26. (currently amended) [[A]] The method according to claim 16, wherein the stripping composition is polymerized by applying heat.

27. (currently amended) [[A]] The method according to claim 26, wherein the polymerization cycle is 1 hour at $150^{\circ}\text{C} \pm 5^{\circ}\text{C}$.

28. (currently amended) [[A]] The method according to claim 26, wherein the polymerization cycle is 30 minutes at 100°C.

29. (currently amended) [[A]] The method according to claim 21, wherein the surface of the mold is coated with a wipe or a cloth impregnated in the stripping composition.

30. (currently amended) [[A]] The method according to claim 29, wherein the stripping composition is polymerized by applying heat.

31. (currently amended) [[A]] The method according to claim 16, ~~in which~~ wherein the composite material part formed in the mold is a helicopter blade or an element of such a blade.